

CAMARO™ LOC

Camaro Loc PUR is a collection of luxury interlocking vinyl flooring tiles, replicating the natural beauty of wood and stone, designed for use in residential interiors.



	Gauge	EN ISO 24346 (EN 428)	4.0mm
	Wear Layer	EN ISO 24340 (EN 429)	0.3mm
	Plank Size	EN ISO 24342 (EN 427)	15 @ 145.6 x 907.6mm = 1.98m ² 9 @ 177.4 x 1212.4mm = 1.94m ²
	Tile Size	EN ISO 24342 (EN 427)	11 @ 298 x 602.8mm = 1.98m ²
	Total Weight	EN ISO 23997 (EN 430)	7025g/m ²
	General Performance	EN 649 EN ISO 10582	Conforms Conforms
	Use Area	EN ISO 10874 (EN 685)	
	Behaviour to Fire	EN 13501-1	Bfl-S1
	Resistance to Chemicals	EN ISO 26987 (EN 423)	Resistant depending on concentration and time of exposure. In case of increased impact of oils, grease, acids, alkalis and other aggressive chemicals, please contact us.
	Abrasion Resistance	EN ISO 10582 (EN 649)	Group T Type 1
	Slip Resistance	EN 13893 DIN 51130 AS 4586	Class DS (dry condition) R10 R10
		For safety flooring with sustainable wet slip resistance, refer to Expona Control or the Polysafe ranges.	
	Residual Indentation	EN ISO 24343-1 (EN 433)	<0.1mm
	Dimensional Stability	EN ISO 23999 (EN 434)	≤0.1%
	Thermal Conductivity	EN 1264-2	Suitable for underfloor heating. Max 27°C.
	Light Fastness	ISO 105-B02	Level ≥6 method A
	Castor Chair (continuous use)	ISO 4918 (EN 425)	Suitable
	Electrical Behaviour (body voltage)	EN 1815	≤2kV Classified as 'antistatic'
	VOC Emissions	Indoor Air Comfort GOLD AgBB VOC test FloorScore Finnish M1 Classification	Eurofins certified product Very low emissions Certified product Pass
	Responsible Sourcing	BES 6001	Good

Environmentally Preferable Flooring - Polyflor Camaro Loc PUR achieves a BRE Global Environmental A+ rating. It is 100% recyclable and contains average 40% recycled material. Recyclable via the Recofloor scheme. Visit www.polyflor.com/sustainability

PUR - Polyflor Camaro Loc PUR features a high quality, cross-linked polyurethane reinforcement, UV cured to provide a low-cost, polish free maintenance regime for the lifetime of the flooring.

For information regarding handling and installation, adhesives, maintenance, applications, chemical resistance and product warranty, consult **Polyflor Customer Technical Services** on +44 (0)161 767 1912, or email tech@polyflor.com. The data presented is correct at the time of printing. For latest information, please visit our website polyflor.com. Decoration and shade may vary slightly from the samples shown.



UK Sales Direct: +44 (0)161 767 1122 | Export Sales Direct: +44 (0)161 767 1913
Sample Requests: +44 (0)161 767 2551 | email: info@polyflor.com | www.polyflor.com

