

bloc

Featuring a single solid colour with a textured emboss, Polyflor Bloc PUR has a 0.70mm pigmented homogeneous PVC wear layer. A high performance, heavy duty heterogeneous sheet floorcovering with a polyurethane reinforcement, Bloc is ideally suited for use within the retail, leisure and commercial sector. The quality of a finished installation of Bloc is dependent upon the preparation of the subfloor which must be smooth. Also the frequency of a regular and well planned maintenance regime should be considered at the outset to ensure the plain floorcovering retains the optimum appearance.



- The flooring shall be Polyflor Bloc PUR, as supplied by Polyflor Ltd of Manchester, England.
- The flooring features a single solid colour with a textured emboss.
- The flooring shall be flexible PVC sheet flooring in 2.00mm thickness.
- It shall have the following laminated construction: 0.7mm pigmented homogeneous PVC wear layer, with a 1.30mm PVC backing featuring a pimple emboss.
- The flooring shall incorporate a specially formulated polyurethane reinforcement.
- As with any plain material, the soil hiding properties are less than similarly coloured patterned floors.
- The frequency of a regular and well planned maintenance regime should be considered at the outset to ensure the plain floorcovering retains the optimum appearance.
- Careful consideration should be given when choosing very light colours in highly trafficked areas.
- The use of a robust and effective dirt barrier system should be considered early in the specification chain.



- In accordance with EN ISO 10582/EN 649, the in-use classification must be at least 23/34/43 as described in EN ISO 10874: ie domestic areas with intense use; commercial areas with very heavy traffic; and heavy light industrial areas.
- In respect of flame spread, the flooring shall have been fully tested to EN13501-1 and certified as having Class Bfl-S1.
- The Binder Content shall be Type I as defined in EN ISO 10582.
- This product does not accumulate static charges above 2kV and is classified as 'antistatic' when tested to EN1815. For specialist applications where there is a requirement to dissipate the electrostatic charge see the Polyflor ESD product ranges.
- With regards the European requirement EN 13893 for slip resistance, the flooring shall be classified DS, making it suitable for use in areas which are predominantly dry. When tested to DIN 51130 the product shall be classified as R10. For safety flooring with sustainable wet slip resistance, refer to the Polysafe ranges.
- In respect of light fastness, the flooring shall have been fully tested to ISO 105-B02 Method 3 as having a pass to ≥6.
- The flooring must be available in 2.01 metre width, including a 0.01 metre selvage for on site trimming, to minimise the number of joints.



- The flooring will achieve a BRE Global Environmental A+ rating (Generic) in the Green Guide to Specification.
- Generic EN 15804 Environmental Product Declaration (EPD) available on request.
- The manufacturer should provide a facility to take back and recycle waste vinyl flooring material through the Recofloor scheme.
- The flooring shall be tested to and pass key independent, international standards for low VOC emissions.



- The supplier of the floorcovering must be in possession of a valid quality systems certificate showing compliance with ISO 9001.
- The supplier of the floorcovering must be in possession of a valid environmental certificate showing compliance with ISO 14001.



- A moisture test must be carried out, to ensure that the subfloor has dried out to a level consistent with the application of vinyl flooring. The test should be carried out, in accordance with the instruction in BS 8203 in the UK and other relevant national standards. The result should not exceed 75%RH, if using a hygrometer, once equilibrium has been achieved.
- The subfloor must have a smooth and even finish to avoid any irregularities becoming visible through the floorcovering.
- Floorcoverings with a plain decoration may require a higher level of subfloor preparation to ensure a quality finish.
- The adhesive used must be approved by Polyflor, to ensure full product compatibility.
- Products must be fully conditioned to the environment in which they are to be installed as outlined by Polyflor. Suitable for use with underfloor heating up to 27°C. See Polyflor installation instructions for details.
- Installation must be carried out in accordance with BS 8203, other relevant national standards and the instructions of Polyflor.
- All joints must be welded. As a single solid colour Bloc PUR should be cold welded whenever a high degree of aesthetic quality is required, or if preferred the seams can be heat welded.



- Polyflor Bloc PUR is recommended for heavy traffic areas that require a hardwearing floorcovering which is attractive and modern and is ideally suited for application within the retail, leisure and commercial sectors.



- At the date of issue the data presented is correct.
- However, Polyflor Ltd reserve the right to make changes which do not adversely affect performance or quality.
- For clarification and for information regarding handling and installation, adhesives, maintenance, applications, chemical resistance and warranty, consult Polyflor Customer Technical Services on +44 (0)161 767 1912, or email tech@polyflor.com.

